

1. PRODUCT NAME:

CRS-2H
SealMaster®/Hawaii

2. CRUDE SOURCE:

Asphalt Hawaii

3. MANUFACTURER:

SealMaster®/Hawaii
2927 Mokumoa Street
Honolulu, HI 96819-4404
Phone: (808) 839-2782
Fax: (808) 839-2002
www.sealmasterhawaii.com

Tank #: Container Pick-Up
Sample Date: 05/01/10
Date Tested: 05/01/10
Sample ID#: CRS-0510
Operator: BP

METHOD	TEST	SPECS MIN / MAX	RESULT
T-59/D-244	Viscosity, SFS @ 122°F. s	75 / 400	86
T-59/D-244	Sodium Dioctyl Sulfosuccinate, %	40 / ...	Pass
T-59/D-244	Storage Stability, 24-h, %	... / 1.0	Pass
T-59/D-244	Sieve, %	... / 0.10	nil
T-59/D-244	Residue by Evaporation, %	65 / ...	69.0
T-59/D-244	Particle Charge	Positive	Pass
T-59/D-244	Oil Distillate, By Volume of Emulsion, %%	... / 3.0	0
TESTS ON RESIDUE FROM DISTILLATION TEST:			
T-49/D-5	Penetration, 77°F	40 / 90	52
T-51/D-113	Ductility, 77°F	40 / ...	Pass
T-44/D-2042	Solubility, %	97/ ...	Pass

These results relate only to the sample(s) tested.
This document shall not be reproduced except in full, without the approval of SealMaster.
Testing performed at the above location.

The above tests meet AASHTO M-208 and ASTM D2397 Requirements for Emulsified Asphalt, and conform to Hawaii Emulsion Specifications.

SealMaster warrants that Product meets the chemical composition and performance requirements set forth in Technical Data. Liability to the buyer or user of this product is limited to the replacement value of the product only.

Copyright © 2010, SealMaster
All Rights Reserved.

SealMaster/Hawaii
Phone: (808) 839-2782
www.sealmasterhawaii.com