

1. **PRODUCT NAME:**
LMCQS-1H
SealMaster®/Hawaii
2. **CRUDE SOURCE:**
Asphalt Hawaii
3. **MANUFACTURER:**
SealMaster®/Hawaii
2927 Mokumoa Street
Honolulu, HI 96819-4404
Phone: (808) 839-2782
Fax: (808) 839-2002
www.sealmasterhawaii.com

METHOD	TEST	MIN	MAX
T-59/D-6933 *	Sieve, %	...	0.10
T-59/D-6934 *	Residue, %	57	...
T-72/D-88	Viscosity, SFS @ 77°F.	20	100
T-59/D-D6930 *	Storage Stability, 24-h, %	...	1.0
T-59/D-7402 *	Particle Charge		Positive
TESTS ON RESIDUE:			
T-49/D-5	Penetration, 0.1mm	40	90
T-51/D-113	Ductility, cm	40	...
T-44/D-2042	Solubility, %	97.5	...

*Formerly part of ASTM D-244

This document shall not be reproduced except in full, without the approval of SealMaster.

The above tests meet AASHTO M-208 and ASTM D-2397 Requirements for Cationic Emulsified Asphalt, and conform to Hawaii Emulsion Specifications.

SealMaster warrants that Product meets the chemical composition and performance requirements set forth in Technical Data. Liability to the buyer or user of this product is limited to the replacement value of the product only.

Copyright © 2011, SealMaster
All Rights Reserved.

SealMaster/Hawaii
Phone: (808) 839-2782
www.sealmasterhawaii.com