

1. PRODUCT NAME:
 LMCRS-2H
 SealMaster®/Hawaii

2. CRUDE SOURCE:
 Asphalt Hawaii

3. MANUFACTURER:
 SealMaster®/Hawaii
 2927 Mokumoa Street
 Honolulu, HI 96819-4404
 Phone: (808) 839-2782
 Fax: (808) 839-2002
 www.sealmasterhawaii.com

Tank #: Container Pick-Up
 Sample Date: 05/01/10
 Date Tested: 05/01/10
 Sample ID#: LMCRS-0510
 Operator: BP

METHOD	TEST	SPECS MIN / MAX	RESULT
T-59/D-244	Viscosity, SFS @ 122°F. s	75 / 400	90
T-59/D-244	Settlement, 5 Days, %	- / 5	
T-59/D-244	Storage Stability, 24-h, %	... / 1.0	0.36
T-59/D-244	Demulsibility, %	40 / ...	
T-59/D-244	Sieve, %	... / 0.30	nil
T-59/D-244	Residue by Evaporation, %	65 / ...	68.4
T-59/D-244	Particle Charge	Positive	Pass
TESTS ON RESIDUE FROM DISTILLATION TEST:			
T-49/D-5	Penetration, 77°F	40 / 90	48
T-51/D-113	Ductility, 77°F	40 / ...	Pass
T-44/D-2042	Solubility, %	97-5 / ...	99.9
T-53/D-36	Softening Point	130 / ...	140

These results relate only to the sample(s) tested.
 This document shall not be reproduced except in full, without the approval of SealMaster.
 Testing performed at the above location.

The above tests meet AASHTO M-140 and ASTM D977 Requirements for Emulsified Asphalt,
 and conform to Hawaii Emulsion Specifications.

SealMaster warrants that Product meets the chemical composition and performance requirements
 set forth in Technical Data. Liability to the buyer or user of this product is limited to the replacement
 value of the product only.

Copyright © 2010, SealMaster
 All Rights Reserved.

SealMaster/Hawaii
 Phone: (808) 839-2782
 www.sealmasterhawaii.com