

1. PRODUCT NAME:

SS-1H
 SealMaster®/Hawaii

2. CRUDE SOURCE:

Asphalt Hawaii

3. MANUFACTURER:

SealMaster®/Hawaii
 2927 Mokumoa Street
 Honolulu, HI 96819-4404
 Phone: (808) 839-2782
 Fax: (808) 839-2002
 www.sealmasterhawaii.com

**** SAMPLE ONLY ****
 Current certificate available upon purchase

SS-1H
 SealMaster®/Hawaii
 SMH - 006
 SealMaster®/Hawaii

METHOD	TEST	SPECS MIN / MAX	TYPICAL RESULT
T-59/D-6933*	Sieve, %	... / 0.10	0.01
T-59/D-6997*	Residue, %	57 / ...	61.8
T-72/D-88	Viscosity, SFS @ 77°F, s	20 / 100	32
T-59/D-6935*	Cement Mixing, %	... / 2.0	0.1
T-59/D-6930*	Storage Stability, 24-h, %	... / 1.0	0.3
TESTS ON RESIDUE:			
T-49/D-5	Penetration, 0.1mm	40 / 90	56
T-51/D-113	Ductility, cm	40 / ...	100
T-44/D-2042	Solubility in TCE, %	97.5 / ...	98.5

*Formerly part of ASTM D-244

These are typical results obtained from samples tested. They do not relate to a specific sample. Current results may be obtained when purchasing product.

The above tests meet AASHTO M-140 and ASTM D977 Requirements for Emulsified Asphalt and conform to Hawaii Emulsion Specifications.

SealMaster warrants that Product meets the chemical composition and performance requirements set forth in Technical Data. Liability to the buyer or user of this product is limited to the replacement value of the product only.

This document shall not be reproduced except in full, without the approval of SealMaster.

Copyright © 2012, SealMaster
 All Rights Reserved.

SealMaster/Hawaii
 Phone: (808) 839-2782
 www.sealmasterhawaii.com